



TimeSaver SR™/MC

Ultra High Solids Finish

An ultra-high solids scrub and recoat finish that does exactly what it says — saves time and money

Labor Savings

- Requires fewer initial coats and typically only one coat when recoating to achieve a high gloss appearance level

Easy to Use

- No special applicator or equipment required
- Grab your mop and bucket and you're ready to go

Superior Gloss

- Provides excellent initial gloss and gloss retention, even with fewer coats

Excellent Durability

- Exceptional resistance to scratching, scuffing and black heel marks

Low Odor

- Ideal for use in patient rooms, busy hallways, aisles and 24 hour facilities

Designed For

EDUCATION

RETAIL

GOVERNMENT



Use Overview:

TimeSaver SR™/MC Ultra High Solids Finish is for use on all resilient floors. Prior to use on non-resilient surfaces like terrazzo, quarry tile or concrete, test the finish for adhesion. When initially applied, finish appears milky white due to the unique formula. However, this will disappear and be clear when dry.

- Blockade areas to be stripped or finished. Floors will be very slippery until dry.
- Strip floor using a JohnsonDiversey stripper per the instructions on the stripper label.

Coating

- Using a clean mop, apply a maximum of 3 medium coats of **TimeSaver SR™/MC Ultra High Solids Finish**. After 24-hours, additional coats may be applied until desired gloss is achieved.
- Allow 30–40 minutes drying time between coats. Temperature, humidity and ventilation may affect drying time. Allow finish to cure for 24-hours before burnishing or applying extra coats. Apply no more than 3 coats in a 24-hour period.

Maintenance

- Dust mop or sweep.
- Clean the floor with a mop or an automatic scrubber using the recommended JohnsonDiversey brand cleaner according to label directions.



- To enhance appearance, use any of the following methods: Spraybuff with Snapback™ SprayBuff, a red pad, and 175–1500 rpm equipment. Dry buff using a medium to aggressive pad and 1000–1500 rpm equipment. Ultra-high speed burnish using a medium to aggressive pad and 2000 rpm equipment.

Recoating

- Dust mop or sweep.
- Clean the floor with a mop or an automatic scrubber using the recommended JohnsonDiversey brand cleaner according to label directions.
- Blockade area and apply 1–2 uniform coats of finish using a clean mop. Allow finish to cure for 24 hours before burnishing.

Product Specifications:

Color/Form	Milky white
Coverage	2000–2500 sq. ft./gallon
Dry Time	Approximately 30–40 minutes
pH	8.0–8.4
Scent	Mild

Shelf Life	2 years
Slip Resistance	0.5 minimum (ASTM D2047)
Solids (Non-Volatile)	30.5%–31.5%
Specific Gravity	1.08
Weight	8.69 lbs./gallon

Two convenient sizes:

PRODUCT CODE	DESCRIPTION/PACKAGE SIZE	DILUTION
3137723	4 x 1 gallon / 3.78 L Containers	Ready-To-Use
5104984	1 x 5 gallon / 18.9 L Envirobox™/MC	Ready-To-Use

Hazard Rating:

HMIS		NFPA
1	Health	1
0	Flammability	0
0	Reactivity	0

4=Very High; 3=High; 2=Moderate; 1=Slight; 0=Insignificant.

Safety Reminder:

Please make sure your employees read and understand the product label and Material Safety Data Sheet before using this product. The label contains directions for use, and both the label and MSDS contain hazard warnings, precautionary statements and first aid procedures. MSDSs are available on-line at www.johnsondiversey.com or by calling 1-888-352-2249.